

## Cee-Bee<sup>®</sup> E-3102

Cee-Bee<sup>®</sup> E-3102 is a non-toxic, alkaline mold release agent remover designed for dissolving build-up of silicone-based mold release agents and epoxy fiber resin from composite tooling.

### Conforms To

- Spirit Aerosystems

### Benefits

- Contains no halogenated solvents, phenol or heavy metals.
- Provides excellent removal of silicone-based mold release agents.
- Thixotropic - Clings to vertical, inclined and bowed/curved surfaces.
- Safe on Bismaleimide (BMI) composite and Invar metal tooling substrates.
- Reduces the need for manual sanding to remove mold release coatings, resulting in significant time savings.

### Properties

- Viscous liquid
- Mild odor

### Notes Prior to Handling

Before using your Cee-Bee<sup>®</sup> products, all safety and operating instructions should be read and understood. If you have any questions, please contact your Cee-Bee<sup>®</sup> representative before proceeding.

## Use Procedure

---

### Equipment Recommendation

- Use a high-pressure (5:1 or higher) air-activated pump equipped with a 0.5 in. (1.3 cm) inside diameter high-pressure hose and spray wand with a fan-type spray nozzle.
- Use a fan-type spray nozzle for this application.
- Apply the remover cleaner using a pump inlet pressure between 50 to 110 psi.

### Application

1. Optimum performance is attained at temperatures between 70-75°F (21-24°C).
2. Recirculate via pump delivery system of the Cee-Bee<sup>®</sup> E-3102 at least 10 minutes prior to application.
3. The surface to be stripped should be power-rinsed with water to remove light dust or other contamination prior to remover application.
4. Spray, brush or roll an even, light or medium coating of remover, starting from the bottom of the tooling/call sheet working upward on a vertical surface.
5. The remover may be agitated with a Scotch Brite pad or nylon brush to reduce removal time.  
(Optional)
6. Allow Cee-Bee<sup>®</sup> E-3102 to dwell on the composite mold/tool a minimum of 5 hours depending on the concentration of the contamination of residue buildup, reapplying a light mist coat as required to prevent drying out of initial application.
7. Repeat application if a water-break free surface is not attained.
8. Thoroughly power-rinse the surface with water at ambient temperature after achieving a water-break free surface.
9. Heavy buildup of epoxy resins may require light agitation with a Scotch Brite pad followed by a solvent wipe for total removal.
10. The composite mold surface may be air-dried using filtered forced-air.

## Safety, Handling, and Precautions

- Skin or eye contact can cause irritation.
- Chemical goggles, face shield plus half face respirator or full-face respirator, chemical-resistant gloves and protective clothing sufficient to avoid contact are recommended. See SDS for additional information.
- In case of accidental contact, flush affected area thoroughly with water. If irritation persists, seek medical attention.
- Do not take internally.
- Use in well-ventilated areas.
- Do not mix with other strippers or materials containing chromium.
- **Spent drums from Cee-Bee<sup>®</sup> E-3102 should be thoroughly rinsed before disposal.**
- **If used stripper is placed back into the original Cee-Bee<sup>®</sup> E-3102 drums, these drums MUST first be rinsed thoroughly.**
- **Store Cee-Bee<sup>®</sup> E-3102 in a temperature range of 50-90°F (10-32°C).**

## Contact Us

---

### United States

#### McGean

Phone: +1-216-441-4900

Fax: +1-216-441-1377

Email: [Aviation@McGean.com](mailto:Aviation@McGean.com)

### United Kingdom

#### McGean-Rohco (UK) Ltd.

Phone: +44-1902-456563

Fax: +44-1902-457443

Email: [Aviation@McGean-Rohco.co.uk](mailto:Aviation@McGean-Rohco.co.uk)

---

### Singapore

#### McGean Singapore

Phone: +65-6863-2296

Fax: +65-6863-2297

Email: [Info@ceebee.com.sg](mailto:Info@ceebee.com.sg)

### China

#### Cee-Bee Aviation Materials (Xiamen) Co. Ltd.

Phone: +86-592-551-3689

Email: [Info@ceebee.com.cn](mailto:Info@ceebee.com.cn)

**Cee-Bee<sup>®</sup> E-3102** is a non-toxic, alkaline mold release agent remover designed for dissolving build-up of silicone based mold release agents and epoxy fiber resin from composite tooling.

**CAUTION:** BEFORE USING ANY OF THESE PRODUCTS, YOU MUST BECOME COMPLETELY FAMILIAR WITH THE INFORMATION CONTAINED IN MCGEAN'S SAFETY DATA SHEETS. All information contained therein or in this document regarding handling, personal protection, and other safety measures must be followed during use. McGean presents the information herein without warranty and disclaims any liability, including any consequential, special, or indirect damages, arising from its use and misuse. Because the use, the conditions of use, product or product composition, and/or applicable laws may differ from one location to another and/or may change with time, the purchaser and/or user is solely responsible for determining whether the product is appropriate for use. McGean recommends use of this product solely in commercial processes which are specified by McGean and which do not violate any third-party patent rights or any laws or regulations or otherwise adversely impact human health and the environment. Users must make their own investigations and determine the suitability of the product for their particular purposes. McGean does not guarantee the accuracy of any data provided by its suppliers. MCGEAN MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE EXCEPT AS EXPRESSLY STATED IN THE SELLER'S SALES CONTRACT OR SALES ACKNOWLEDGEMENT FORM. USE OF ANY MCGEAN PRODUCT IS AT THE USER'S RISK.



Revision: 06/2021 (Rev. A2)